






Cottostone palladiana

TECHNICAL CHARACTERISTICS

Technical data

technical characteristics	norms	EN-norm values	Sannini values
---------------------------	-------	----------------	----------------

	apparent volumic mass	EN W I	$M_V=2192\text{kg/m}^3$
	water absorption	EN W I	$C=0,5\%$
	flexural strenght	EN W I	$R_{tf}=(33,2\pm 2,4)\text{MPa}$
	linear thermal expansion	UNI EN 202	coefficient linear thermal expansion from ambient temperature $<10 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$ $1,9 \times 10^{-6}/^\circ\text{C}$
	sliding resistance	DIN 51130	test on inclined plan R 11