


















CottoFlash Litos

TECHNICAL CHARACTERISTICS

Technical data

technical characteristics	norms	EN-norm values	Sannini values
 length	UNI EN 98	± 1,5% max.	corresponding
 thickness	UNI EN 98	± 10% max.	corresponding
 straightness of sides	UNI EN 98	± 10% max.	corresponding
 rectangularity	UNI EN 98	± 1,5% max.	corresponding
 surface flatness centre curvature	UNI EN 98	± 1% max.	corresponding
 surface flatness edge curvature	UNI EN 98	± 1% max.	corresponding
 surface flatness warpage	UNI EN 98	± 1,5% max.	corresponding
 surface quality	UNI EN 98	percentage of acceptable files in the lot free visible defects 95 min.	corresponding
 water absorption	UNI EN 99	average value $3 < E \leq 6$	4,6
 modulus of ropture	UNI EN 100	average value $> 10 \text{ N/mm}^2$	$> 20 \text{ N/mm}^2$
 scratch hardness of surface (Mohs)	UNI EN 101	unglazed tiles 5 min.	5
 abrasion resistance	UNI EN 102	removed volume in mm^3 771 max.	511 mm^3
 res. to household chemical swimming pool water cleansers	ISO 10545	free of visible defects	not resistant
 resistance to acid and alkalis	ISO 10545	unglazed tiles	not resistant
 frost resistance	UNI EN 202	free of visible defects	not resistant
 sliding resistance	DIN 51130	test on inclined plan	R9
 static coefficient of friction	ASTM/C 1028	on dry surface on wet surface	0,76 0,74